



# Adhesive Transfer Tapes with Adhesive 300LSE

9453LE • 9471LE • 9472LE

Technical Data

September, 2002

---

**Product Description:**

- 3M™ Adhesive 300LSE is a hi-strength acrylic adhesive that provides a very high bond strength to most surfaces.
- Excellent bond to low surface energy plastics, such as polypropylene and powder coatings.
- Excellent adhesion to lightly oiled surfaces typical of machine parts.
- Thickness range of 2.0 mils, 3.5 mils and 5.0 mils for use on smooth, rough and textured surfaces.
- Extremely smooth adhesive for excellent graphics appearance.
- Polycoated kraft liner for die-cutting end tabs and waste removed nameplates on a common carrier.

---

**Product Construction:**

	<b>Tape 9453LE</b>	<b>Tape 9471LE</b>	<b>Tape 9472LE</b>
Adhesive: (Solvent Free)	3.6 mils (91 microns) 3M High-strength Acrylic Adhesive 300LSE	2.3 mils (58 microns) 3M High-strength Acrylic Adhesive 300LSE	5.2 mils (132 microns) 3M High-strength Acrylic Adhesive 300LSE
Liner:	4.2 mils (107 microns) 58# Polycoated kraft	4.2 mils (107 microns) 58# Polycoated kraft	4.2 mils (107 microns) 58# Polycoated kraft

# 3M™ Adhesive Transfer Tapes with Adhesive 300LSE

9453LE • 9471LE • 9472LE

---

## Typical Physical Properties and Performance Characteristics:

### Typical Adhesion Properties

**Note:** The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Peel Adhesion - ounces/inch (Newtons/100 mm) ASTM D3330, modified: 90° peel, 2 mil aluminum backing.

### Typical Adhesion Chart

	3M™ Adhesive Transfer Tape	15 Minute Room Temperature		72 Hour Room Temperature	
		Oz./In.	N/100 mm	Oz./In.	N/100 mm
Stainless Steel	9453LE	90	98	100	109
	9471LE	71	78	75	82
	9472LE	109	119	140	153
ABS	9453LE	80	88	113	124
	9471LE	70	77	79	86
	9472LE	102	112	128	140
Polypropylene	9453LE	89	97	103	113
	9471LE	69	75	74	81
	9472LE	115	126	136	149

The properties defined are based on the attachment of impervious faceplate materials (such as aluminum) to a stainless steel test surface.

**Bond Build-up:** The bond strength of 3M™ Adhesive 300LSE increased as a function of time and temperature, and has very high initial adhesion.

**Humidity Resistance:** High humidity has minimal effect on adhesive performance. No significant reduction in bond strength is observed after exposure for 7 days at 90°F (32°C) and 90% relative humidity.

**U.V. Resistance:** When properly applied, nameplates and decorative trim parts are not adversely affected by exposure.

**Water Resistance:** Immersion in water has no appreciable effect on the bond strength. After 100 hours at room temperature, the high bond strength is maintained.

**Temperature Cycling Resistance:** High bond strength is maintained after cycling four times through:

- 4 hours at 158°F (70°C)
- 4 hours at -20°F (-29°C)
- 4 hours at 73°F (22°C)

**Chemical Resistance:** When properly applied, nameplate and decorative trim parts will hold securely after exposure to numerous chemicals including oil, mild acids and alkalis.

**Temperature Resistance:** Adhesive 300LSE is usable for short periods (minutes, hours) at room temperatures up to 300°F (148°C) and for intermittent longer periods of time (days, weeks) up to 200°F (93°C).

**Lower Service Temperature:** -40°F (-40°C).

# 3M™ Adhesive Transfer Tapes with Adhesive 300LSE

9453LE • 9471LE • 9472LE

**Available Sizes:**

Width and Length (subject to minimum order requirements):	
Limitations:	1/2 in. to 63/64 in.: Maximum 180 yards 1 in. to 54 in.: Maximum 360 yards
Minimum Slit Width:	1/2 in.
Maximum Slit Width:	54 in.
Normal Slitting Tolerance:	± 1/32 in.
Core	3.0 in.

**Application Techniques:**

For maximum bond strength, the surface should be thoroughly cleaned and dried. Typical cleaning solvents are heptane or isopropyl alcohol. Carefully read and follow manufacturer’s precautions and directions for use when using cleaning solvents.

Bond strength can also be improved with firm application pressure and moderate heat, from 100°F (38°C) to 130°F (54°C), causing the adhesive to develop intimate contact with the bonding surface.

Ideal tape application temperature range is 70°F to 100°F (21°C to 38°C). Initial tape application to surfaces at temperatures below 50°F (10°C) is not recommended for most pressure-sensitive adhesives because the adhesive becomes too firm to adhere readily. However, once properly applied, low temperature holding is generally satisfactory.

**General Information:**

- Plastic nameplates or graphic overlays for use on low surface energy plastics.
- Waste removed nameplates on a common sheet for ease of application.
- Attaching membrane switch assemblies to powder coated surfaces and low surface energy plastics.
- Graphic overlays with end tabs for easy liner removal.
- Graphic application to surfaces such as wood, fabric, plastic, where very high bond strength is required.
- Attaching identification material to lightly oily surfaces typical of machine parts.

**Application Ideas:**

**Processing:**

**Slitting and die-cutting:** This adhesive is very aggressive and may be difficult to convert depending on your application requirements. Chilling the adhesive between 35°F and 50°F will improve the processability. In addition, dies can be lubricated with Laminoleum evaporative stamping oil, which is available from Metal Lubricants Company (708-333-8900), or with Lubri-Blade 907 from Ceramic Technologies Inc. (800-258-8495). You may also refer to our Technical Bulletin on 300LSE converting. (70-0707-6205-2)

**Roll Laminating:** A combination of metal and rubber rollers with moderate pressure is recommended.

**Note:** Please refer to the Technical Bulletin on slitting. (70-0709-3905-6)

# 3M™ Adhesive Transfer Tapes with Adhesive 300LSE

9453LE • 9471LE • 9472LE

---

**Shelf Life:** Product retains its performance and properties for two years from date of manufacture if properly stored at room temperature conditions of 72°F (22°C) and 50% relative humidity. Storage in plastic bag is recommended

---

**For Additional Information** To request additional product information or to arrange for sales assistance, call toll free 1-800-223-7427 or visit [www.3M.com/converter](http://www.3M.com/converter). Address correspondence to: 3M Engineered Adhesives Division, 3M Center, Building 220-7E-01, St. Paul, MN 55144-1000. Our fax number is 651-733-9175. In Canada, phone: 1-800-364-3577. In Puerto Rico, phone: 1-787-750-3000. In Mexico, phone: 52-70-04-00.

---

**Important Notice** 3M MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. User is responsible for determining whether the 3M product is fit for a particular purpose and suitable for user's method of application. Please remember that many factors can affect the use and performance of a 3M product in a particular application. The materials to be bonded with the product, the surface preparation of those materials, the product selected for use, the conditions in which the product is used, and the time and environmental conditions in which the product is expected to perform are among the many factors that can affect the use and performance of a 3M product. Given the variety of factors that can affect the use and performance of a 3M product, some of which are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method of application.

---

**Limitation of Remedies and Liability** If the 3M product is proved to be defective, THE EXCLUSIVE REMEDY, AT 3M'S OPTION, SHALL BE TO REFUND THE PURCHASE PRICE OF OR TO REPAIR OR REPLACE THE DEFECTIVE 3M PRODUCT. 3M shall not otherwise be liable for loss or damages, whether direct, indirect, special, incidental, or consequential, regardless of the legal theory asserted, including, but not limited to, contract, negligence, warranty, or strict liability.



This Engineered Adhesives Division product was manufactured under a 3M quality system registered to ISO 9002 standards.



**Converter Markets  
Engineered Adhesives Division**

3M Center, Building 551-1W-02  
St. Paul, MN 55144-1000



*Recycled Paper*  
40% pre-consumer  
10% post-consumer

Printed in U.S.A.  
©3M 2002 70-0707-7533-6 (9/02)